

**NORTHERN GREECE CERAMICS S.A.**

Nea Santa 61100 - Kilkis, Greece

Tel: 0030 23410 75570

Fax: 0030 23410 75574

Email: info@kebe-sa.gr

web: www.kebe-sa.gr

EST. 1935

KOTHALI

**KEBE**

NORTHERN GREECE CERAMICS

19**EN 771-1:2011+A1:2015****ORTHOBLOCK MK200****Vertically Perforated Clay Masonry unit P, for use in protected masonry,
Category II**

DOP Reference No	MK200-25	
Length	380	mm
Width	200	mm
Height	240	mm
Dimensional tolerance	T1	
Range category	R1	
Flatness of bed faces	≤1	mm
Plane parallelism of bed faces	≤1	mm
Configuration	As in attached drawing	
Gross dry density	680	kg/m ³
Net dry density	1900	kg/m ³
Density tolerance	D1:10	%
Mean compressive strength (perpendicular to bed face)	7,0	N/mm ²
Category	II	
Bond strength (Tabulated value acc.to EN 998-2 Annex C)	0,30	N/mm ²
Thermal conductivity $\lambda_{10,dry,unit}$ (P3)	0,1971	W/mK
Thermal conductivity $\lambda_{equ,design,masonry}$ (with 3mm mortar joints)	0,2193	W/mK
Water vapour permeability μ	5/10	
Durability against freeze/thaw	F0	
Water absorption	NPD	
Active soluble salt content	S0	
Reaction to fire : Euroclass	A1	
Dangerous substances	NPD	

Particular conditions applicable to the use:

Cutting with power tools may generate dust. People undertaking works of this nature are advised to wear suitable personal protective equipment (PPE)

